

Average performance values of SGU (6mm, Coating Face #2)
 Average performance values of DGU (6mm | 12 Air | 6mm)
 with coating on surface #2, according to EN standard.



| Product Family | Product | Application | Light Factor | | | Energy Factors | | |
|----------------------|-----------------------|-------------|----------------------------|------------------------------------|------------------------------------|---------------------------|--------------------------|-------------------------------|
| | | | Light Transmittance LT (%) | External Light Reflectance LRe (%) | Internal Light Reflectance LRI (%) | Solar Factor g-value (SF) | Shading Coefficient (SC) | U-value (W/m ² .K) |
| NEUTRAL | | | | | | | | |
| SOLAR CONTROL | COOL-LITE® ST 167 | SGU | 67 | 19 | 19 | 0.68 | 0.78 | 5.6 |
| | COOL-LITE® ST 150 | SGU | 51 | 18 | 17 | 0.56 | 0.64 | 5.6 |
| | COOL-LITE® ST 136 | SGU | 37 | 22 | 18 | 0.43 | 0.5 | 5.5 |
| | COOL-LITE® ST 120 | SGU | 20 | 32 | 27 | 0.29 | 0.33 | 5.2 |
| | COOL-LITE® ST 108 | SGU | 9 | 43 | 34 | 0.14 | 0.16 | 3.6 |
| | COOL-LITE® ST 167 | DGU | 60 | 22 | 23 | 0.6 | 0.68 | 2.8 |
| | COOL-LITE® ST 150 | DGU | 46 | 20 | 22 | 0.47 | 0.54 | 2.8 |
| | COOL-LITE® ST 136 | DGU | 34 | 23 | 23 | 0.35 | 0.4 | 2.7 |
| | COOL-LITE® ST 120 | DGU | 18 | 32 | 30 | 0.21 | 0.25 | 2.6 |
| | COOL-LITE® ST 108 | DGU | 8 | 43 | 36 | 0.1 | 0.11 | 1.9 |
| | COOL-LITE® SCN 145 | SGU | 44 | 24 | 7 | 0.45 | 0.52 | 5 |
| | COOL-LITE® SCN 125 | SGU | 29 | 35 | 6 | 0.31 | 0.36 | 4.8 |
| | COOL-LITE® SCN 145 | DGU | 40 | 26 | 14 | 0.37 | 0.43 | 2.6 |
| | COOL-LITE® SCN 125 | DGU | 26 | 36 | 13 | 0.25 | 0.28 | 2.5 |
| | COOL-LITE® ET 151 II | SGU | 51 | 13 | 8 | 0.43 | 0.5 | 4.3 |
| | COOL-LITE® ET 150 | SGU | 50 | 13 | 11 | 0.5 | 0.58 | 5 |
| | COOL-LITE® ET 135 | SGU | 34 | 23 | 8 | 0.34 | 0.39 | 3.9 |
| | COOL-LITE® ET 127 II | SGU | 27 | 11 | 11 | 0.27 | 0.31 | 3.8 |
| | COOL-LITE® ET 125 | SGU | 28 | 28 | 9 | 0.29 | 0.34 | 3.8 |
| | COOL-LITE® ET 151 II | DGU | 46 | 16 | 14 | 0.36 | 0.42 | 2.3 |
| | COOL-LITE® ET 150 | DGU | 45 | 15 | 17 | 0.42 | 0.49 | 2.5 |
| COOL-LITE® ET 135 | DGU | 31 | 24 | 14 | 0.28 | 0.32 | 2.1 | |
| COOL-LITE® ET 127 II | DGU | 24 | 12 | 17 | 0.21 | 0.24 | 2 | |
| COOL-LITE® ET 125 | DGU | 25 | 29 | 15 | 0.23 | 0.27 | 2 | |
| SINGLE SILVER | COOL-LITE® KT 164 | DGU | 57 | 14 | 10 | 0.47 | 0.54 | 1.9 |
| | COOL-LITE® KT 155 | DGU | 47 | 17 | 11 | 0.38 | 0.43 | 1.9 |
| | COOL-LITE® KT 140 II | DGU | 37 | 23 | 12 | 0.29 | 0.33 | 1.8 |
| | COOL-LITE® KN 130 II | DGU | 31 | 22 | 14 | 0.25 | 0.29 | 1.8 |
| | COOL-LITE® KN 125 II | DGU | 24 | 22 | 17 | 0.21 | 0.24 | 1.7 |
| | COOL-LITE® KS 130 II | DGU | 30 | 44 | 19 | 0.22 | 0.25 | 1.6 |
| | COOL-LITE® KS 138 II | DGU | 36 | 38 | 20 | 0.26 | 0.3 | 1.6 |
| | COOL-LITE® KS 146 II | DGU | 42 | 33 | 19 | 0.29 | 0.34 | 1.6 |
| DOUBLE SILVER | COOL-LITE® SKN 183 II | DGU | 74 | 12 | 13 | 0.4 | 0.46 | 1.5 |
| | COOL-LITE® SKN 176 II | DGU | 69 | 13 | 15 | 0.37 | 0.43 | 1.5 |
| | COOL-LITE® SKN 165 II | DGU | 60 | 16 | 18 | 0.34 | 0.39 | 1.5 |

Average performance values of SGU (6mm, Coating Face #2)
 Average performance values of DGU (6mm | 12 Air | 6mm)
 with coating on surface #2, according to EN standard.



| Product Family | Product | Application | Light Factor | | | Energy Factors | | |
|----------------------|-----------------------|-------------|----------------------------|------------------------------------|------------------------------------|---------------------------|--------------------------|-------------------------------|
| | | | Light Transmittance LT (%) | External Light Reflectance LRe (%) | Internal Light Reflectance LRI (%) | Solar Factor g-value (SF) | Shading Coefficient (SC) | U-value (W/m ² .K) |
| | COOL-LITE® SKN 152 II | DGU | 49 | 18 | 14 | 0.27 | 0.31 | 1.6 |
| | COOL-LITE® SKN 146 II | DGU | 40 | 11 | 11 | 0.25 | 0.29 | 1.6 |
| | COOL-LITE® SKN 144 II | DGU | 41 | 20 | 15 | 0.24 | 0.27 | 1.6 |
| | COOL-LITE® SKN 133 II | DGU | 30 | 13 | 10 | 0.19 | 0.22 | 1.6 |
| GREEN | | | | | | | | |
| SOLAR CONTROL | COOL-LITE® ST 467 | SGU | 55 | 14 | 18 | 0.5 | 0.57 | 5.6 |
| | COOL-LITE® ST 450 | SGU | 42 | 14 | 17 | 0.43 | 0.49 | 5.6 |
| | COOL-LITE® ST 436 | SGU | 31 | 17 | 18 | 0.35 | 0.41 | 5.5 |
| | COOL-LITE® ST 420 | SGU | 17 | 23 | 27 | 0.27 | 0.31 | 5.2 |
| | COOL-LITE® ST 408 | SGU | 7 | 31 | 34 | 0.15 | 0.18 | 3.6 |
| | COOL-LITE® ST 467 | DGU | 50 | 17 | 23 | 0.4 | 0.46 | 2.8 |
| | COOL-LITE® ST 468 | DGU | 38 | 15 | 22 | 0.33 | 0.37 | 2.8 |
| | COOL-LITE® ST 469 | DGU | 28 | 17 | 22 | 0.26 | 0.3 | 2.7 |
| | COOL-LITE® ST 470 | DGU | 15 | 24 | 30 | 0.18 | 0.2 | 2.6 |
| | COOL-LITE® ST 471 | DGU | 7 | 31 | 36 | 0.09 | 0.11 | 1.9 |
| | COOL-LITE® SCN 425 | SGU | 23 | 21 | 9 | 0.25 | 0.28 | 3.8 |
| | COOL-LITE® SCN 445 | SGU | 36 | 18 | 7 | 0.36 | 0.42 | 5 |
| | COOL-LITE® SCN 425 | DGU | 17 | 21 | 12 | 0.17 | 0.2 | 2 |
| | COOL-LITE® SCN 445 | DGU | 27 | 19 | 10 | 0.26 | 0.3 | 2.6 |
| | COOL-LITE® ET 451 II | SGU | 42 | 11 | 7 | 0.35 | 0.4 | 4.3 |
| | COOL-LITE® ET 450 | SGU | 41 | 10 | 11 | 0.39 | 0.45 | 5 |
| | COOL-LITE® ET 435 | SGU | 28 | 17 | 7 | 0.27 | 0.32 | 3.9 |
| | COOL-LITE® ET 427 II | SGU | 22 | 9 | 11 | 0.24 | 0.28 | 3.8 |
| | COOL-LITE® ET 425 | SGU | 23 | 21 | 9 | 0.25 | 0.28 | 3.8 |
| | COOL-LITE® ET 451 II | DGU | 38 | 12 | 14 | 0.27 | 0.31 | 2.3 |
| | COOL-LITE® ET 450 | DGU | 38 | 12 | 17 | 0.3 | 0.35 | 2.5 |
| | COOL-LITE® ET 435 | DGU | 25 | 18 | 14 | 0.21 | 0.24 | 2.1 |
| | COOL-LITE® ET 427 II | DGU | 20 | 10 | 17 | 0.17 | 0.19 | 2 |
| | COOL-LITE® ET 425 | DGU | 21 | 21 | 15 | 0.18 | 0.21 | 2 |
| SINGLE SILVER | COOL-LITE® KT 464 | DGU | 47 | 11 | 10 | 0.33 | 0.37 | 1.9 |
| | COOL-LITE® KT 455 | DGU | 39 | 13 | 10 | 0.27 | 0.31 | 1.9 |
| | COOL-LITE® KT 440 II | DGU | 31 | 17 | 12 | 0.22 | 0.25 | 1.8 |
| | COOL-LITE® KN 430 II | DGU | 26 | 16 | 13 | 0.2 | 0.22 | 1.8 |
| | COOL-LITE® KN 425 II | DGU | 20 | 16 | 16 | 0.16 | 0.19 | 1.7 |
| | COOL-LITE® KS 430 II | DGU | 25 | 31 | 19 | 0.18 | 0.2 | 1.6 |

Average performance values of SGU (6mm, Coating Face #2)
 Average performance values of DGU (6mm | 12 Air | 6mm)
 with coating on surface #2, according to EN standard.



| Product Family | Product | Application | Light Factor | | | Energy Factors | | |
|-----------------------|-----------------------|-------------|----------------------------|------------------------------------|------------------------------------|---------------------------|--------------------------|-------------------------------|
| | | | Light Transmittance LT (%) | External Light Reflectance LRe (%) | Internal Light Reflectance LRI (%) | Solar Factor g-value (SF) | Shading Coefficient (SC) | U-value (W/m ² .K) |
| DOUBLE SILVER | COOL-LITE® KS 438 II | DGU | 30 | 28 | 20 | 0.2 | 0.23 | 1.6 |
| | COOL-LITE® KS 446 II | DGU | 35 | 24 | 19 | 0.23 | 0.26 | 1.6 |
| | COOL-LITE® SKN 483 II | DGU | 39 | 9 | 8 | 0.31 | 0.35 | 1.5 |
| | COOL-LITE® SKN 476 II | DGU | 36 | 9 | 8 | 0.29 | 0.33 | 1.5 |
| | COOL-LITE® SKN 465 II | DGU | 32 | 12 | 10 | 0.26 | 0.3 | 1.5 |
| | COOL-LITE® SKN 452 II | DGU | 41 | 14 | 14 | 0.22 | 0.26 | 1.6 |
| | COOL-LITE® SKN 446 II | DGU | 33 | 9 | 11 | 0.2 | 0.24 | 1.6 |
| | COOL-LITE® SKN 444 II | DGU | 22 | 15 | 9 | 0.19 | 0.22 | 1.6 |
| COOL-LITE® SKN 433 II | DGU | 25 | 10 | 10 | 0.16 | 0.19 | 1.6 | |
| BLUE | | | | | | | | |
| SOLAR CONTROL | COOL-LITE® ST 767 | SGU | 42 | 10 | 18 | 0.46 | 0.52 | 5.6 |
| | COOL-LITE® ST 750 | SGU | 32 | 10 | 16 | 0.4 | 0.46 | 5.6 |
| | COOL-LITE® ST 736 | SGU | 23 | 12 | 18 | 0.34 | 0.39 | 5.5 |
| | COOL-LITE® ST 720 | SGU | 13 | 16 | 27 | 0.26 | 0.3 | 5.2 |
| | COOL-LITE® ST 708 | SGU | 6 | 20 | 34 | 0.15 | 0.18 | 3.6 |
| | COOL-LITE® ST 767 | DGU | 38 | 12 | 22 | 0.36 | 0.41 | 2.8 |
| | COOL-LITE® ST 750 | DGU | 29 | 11 | 21 | 0.29 | 0.34 | 2.8 |
| | COOL-LITE® ST 736 | DGU | 21 | 12 | 22 | 0.24 | 0.27 | 2.7 |
| | COOL-LITE® ST 720 | DGU | 12 | 16 | 30 | 0.17 | 0.19 | 2.6 |
| | COOL-LITE® ST 708 | DGU | 5 | 20 | 36 | 0.09 | 0.11 | 1.9 |
| | COOL-LITE® STB 120 | SGU | 22 | 21 | 29 | 0.32 | 0.37 | 5.2 |
| | COOL-LITE® STB 120 | DGU | 13 | 21 | 15 | 0.21 | 0.24 | 2.7 |
| | COOL-LITE® SCN 725 | SGU | 18 | 14 | 9 | 0.23 | 0.27 | 3.8 |
| | COOL-LITE® SCN 745 | SGU | 28 | 12 | 6 | 0.34 | 0.39 | 5 |
| | COOL-LITE® SCN 725 | DGU | 40 | 26 | 14 | 0.37 | 0.43 | 2.6 |
| | COOL-LITE® SCN 745 | DGU | 16 | 13 | 8 | 0.23 | 0.26 | 2.6 |
| | COOL-LITE® ET 75III | SGU | 32 | 8 | 7 | 0.32 | 0.37 | 4.3 |
| | COOL-LITE® ET 750 | SGU | 32 | 8 | 10 | 0.36 | 0.42 | 5 |
| | COOL-LITE® ET 735 | SGU | 21 | 12 | 7 | 0.26 | 0.29 | 3.9 |
| | COOL-LITE® ET 727 II | SGU | 17 | 7 | 11 | 0.23 | 0.26 | 3.8 |
| | COOL-LITE® ET 725 | SGU | 18 | 14 | 9 | 0.23 | 0.27 | 3.8 |
| | COOL-LITE® ET 751 II | DGU | 29 | 9 | 14 | 0.24 | 0.28 | 2.3 |
| | COOL-LITE® ET 750 | DGU | 29 | 9 | 17 | 0.27 | 0.31 | 2.5 |
| | COOL-LITE® ET 735 | DGU | 19 | 12 | 14 | 0.19 | 0.21 | 2.1 |
| | COOL-LITE® ET 727 II | DGU | 15 | 8 | 17 | 0.15 | 0.18 | 2 |
| | COOL-LITE® ET 725 | DGU | 16 | 14 | 15 | 0.16 | 0.19 | 2 |

Average performance values of SGU (6mm, Coating Face #2)
 Average performance values of DGU (6mm | 12 Air | 6mm)
 with coating on surface #2, according to EN standard.



| Product Family | Product | Application | Light Factor | | | Energy Factors | | |
|--|-----------------------|-------------|----------------------------|------------------------------------|------------------------------------|---------------------------|--------------------------|-------------------------------|
| | | | Light Transmittance LT (%) | External Light Reflectance LRe (%) | Internal Light Reflectance LRI (%) | Solar Factor g-value (SF) | Shading Coefficient (SC) | U-value (W/m ² .K) |
| SINGLE SILVER | | | | | | | | |
| | COOL-LITE® KT 764 | DGU | 36 | 8 | 9 | 0.29 | 0.33 | 1.9 |
| | COOL-LITE® KT 755 | DGU | 30 | 10 | 10 | 0.24 | 0.28 | 1.9 |
| | COOL-LITE® KT 740 | DGU | 24 | 12 | 12 | 0.2 | 0.22 | 1.8 |
| | COOL-LITE® KN 730 II | DGU | 20 | 11 | 13 | 0.18 | 0.2 | 1.8 |
| | COOL-LITE® KN 725 II | DGU | 15 | 11 | 16 | 0.15 | 0.17 | 1.7 |
| | COOL-LITE® KS 730 II | DGU | 19 | 20 | 19 | 0.16 | 0.18 | 1.6 |
| | COOL-LITE® KS 738 II | DGU | 23 | 18 | 20 | 0.18 | 0.21 | 1.6 |
| | COOL-LITE® KS 746 II | DGU | 27 | 16 | 19 | 0.2 | 0.23 | 1.6 |
| | COOL-LITE® KBT 140 | DGU | 36 | 24 | 17 | 0.3 | 0.35 | 1.8 |
| | COOL-LITE® KBT 130 II | DGU | 25 | 21 | 22 | 0.22 | 0.25 | 1.7 |
| DOUBLE SILVER | | | | | | | | |
| | COOL-LITE® SKN 783 II | DGU | 30 | 7 | 7 | 0.26 | 0.3 | 1.5 |
| | COOL-LITE® SKN 776 II | DGU | 28 | 7 | 8 | 0.25 | 0.29 | 1.5 |
| | COOL-LITE® SKN 765 II | DGU | 24 | 9 | 9 | 0.23 | 0.26 | 1.5 |
| | COOL-LITE® SKN 752 II | DGU | 31 | 10 | 13 | 0.2 | 0.23 | 1.6 |
| | COOL-LITE® SKN 746 II | DGU | 26 | 7 | 11 | 0.18 | 0.21 | 1.6 |
| | COOL-LITE® SKN 744 II | DGU | 17 | 11 | 9 | 0.17 | 0.2 | 1.6 |
| | COOL-LITE® SKN 733 II | DGU | 19 | 8 | 10 | 0.15 | 0.17 | 1.6 |
| BRONZE / COPPER | | | | | | | | |
| SOLAR CONTROL | | | | | | | | |
| | COOL-LITE® STBRZ 130 | SGU | 29 | 18 | 7 | 0.34 | 0.39 | 5.1 |
| | COOL-LITE® STBRZ 130 | DGU | 26 | 19 | 13 | 0.26 | 0.3 | 2.6 |
| | COOL-LITE® STC 135 | SGU | 38 | 10 | 25 | 0.47 | 0.54 | 5.2 |
| | COOL-LITE® STC 135 | DGU | 35 | 11 | 29 | 0.39 | 0.45 | 2.6 |
| SINGLE SILVER | COOL-LITE® KBRZ 127II | DGU | 27 | 19 | 17 | 0.22 | 0.25 | 1.6 |
| GOLD | | | | | | | | |
| SOLAR CONTROL | | | | | | | | |
| | COOL-LITE® STG 127 | SGU | 27 | 27 | 10 | 0.33 | 0.38 | 5.1 |
| | COOL-LITE® STG 127 | DGU | 24 | 28 | 17 | 0.26 | 0.3 | 2.6 |
| SINGLE SILVER | COOL-LITE® KG 122II | DGU | 22 | 23 | 34 | 0.22 | 0.25 | 1.6 |
| ROSE | | | | | | | | |
| SOLAR CONTROL | | | | | | | | |
| | COOL-LITE® STR 135 | SGU | 36 | 9 | 28 | 0.47 | 0.54 | 5.1 |
| | COOL-LITE® STR 135 | DGU | 33 | 10 | 31 | 0.39 | 0.45 | 2.6 |
| HIGH LIGHT TRANSMISSION LOW-E GLASS | | | | | | | | |
| LOW-E | | | | | | | | |
| | Planitherm 1.3T | DGU | 75 | 12 | 12 | 0.54 | 0.62 | 1.5 |
| | Planitherm Ultra N II | DGU | 78 | 12 | 12 | 0.58 | 0.66 | 1.6 |